

Available Online at www.jourcc.comJournal homepage: www.JOURCC.com

Journal of Composites and Compounds

Recent advances in the synthesis of BiFeO₃ composites as photocatalysis: challenges and opportunities

Marzieh Fattahi ^{a*}

^a Department of Chemistry, Amirkabir University of Technology, 15875-4413 Tehran, Iran

ABSTRACT

Bismuth ferrite (BiFeO₃) is a widely studied multiferroic material with strong ferroelectric and magnetic properties, making it highly suitable for applications in sensors, actuators, and energy storage. The development of BiFeO₃ composites has gained significant attention due to their enhanced functional properties compared to pure BiFeO₃. Various synthesis techniques, including sol-gel processing, hydrothermal synthesis, and solid-state reactions, have been explored to optimize structural, electrical, and magnetic characteristics. The review also explores the applications of BiFeO₃ composites as photocatalysis, highlighting recent breakthroughs and potential future directions. This overview provides insights into the current state of BiFeO₃ composite synthesis and its implications for advancing multiferroic materials in modern technology.

©2023 UGPH.

Peer review under responsibility of UGPH

ARTICLE INFORMATION

Article History:

Received 27 June 2023

Received in Revised form 17 August 2023

Accepted 25 September 2023

Keywords:

BiFeO₃

Multiferroic material

Composites

Synthesis

1. Introduction

Bismuth ferrite (BiFeO₃) is a prominent multiferroic material known for its unique combination of ferroelectric and magnetic properties, making it suitable for various applications, including sensors, actuators, and energy storage devices [1, 2]. The synthesis of BiFeO₃ composites has garnered significant attention due to their enhanced functional properties compared to pure BiFeO₃ [3, 4]. Recent studies highlight the potential of composite structures to improve the material's performance by optimizing the interface between different phases, leading to better magnetoelectric coupling and overall functionality [5-7].

The importance of BiFeO₃ composites lies in their ability to exhibit superior properties through the integration of various materials. For instance, composites formed with materials like Bi₄Ti₃O₁₂ have shown promising results in achieving enhanced multiferroic responses due to the compatibility of their crystal structures, which allows for effective coupling at the interface [2]. Furthermore, advancements in synthesis techniques such as sol-gel methods and hydrothermal synthesis has facilitated the production of high-quality BiFeO₃ composites with tailored [8].

The synthesis process plays a critical role in determining the physical and chemical properties of BiFeO₃ composites [9]. Variations in synthesis methods can lead to differences in microstructure, phase purity, and crystallinity, all of which significantly influence the material's performance. For example, thin film processing techniques have been shown to enhance the remanent polarization and magnetization of BiFeO₃ due to strain effects introduced by substrate interactions during growth [10, 11]. Moreover, doping strategies during synthesis can further modify the electrical and magnetic characteristics of BiFeO₃ composites. The incorporation of dopants such as samarium has been reported to enhance the multiferroic response by improving the alignment of magnetic moments [12, 13]. Consequently, understanding and optimizing the synthesis conditions is essential for developing BiFeO₃ composites with desired properties for specific applications [14, 15]. The ongoing research into BiFeO₃ composites emphasizes the significance of synthesis techniques in tailoring material properties, which is crucial for advancing their practical applications in modern technology [16]. This review aims to synthesize recent

* Corresponding author: Marzieh Fattahi, Email Corresponding author: Mzfatahi@aut.ac.ir

<https://doi.org/10.61186/jcc.5.35> This is an open access article under the CC BY license (<https://creativecommons.org/licenses/by/4.0>)

findings regarding the synthesis methods, application, challenges, and opportunities associated with BiFeO₃ composites.

2. Synthesis Methods of BiFeO₃ Composites

BiFeO₃ composites are of significant interest due to their unique multiferroic properties, which combine ferroelectricity and magnetism [9, 17]. The synthesis of these composites can be achieved through various methods, each offering distinct advantages and challenges. This review discusses the prominent synthesis methods for BiFeO₃ composites, reported recent advancements, and the implications of these techniques. Fig.1 illustrates a type of methods for the synthesis of BiFeO₃.




Fig. 1. Methods of synthesis of BiFeO₃ composite.

2.1. Sol-Gel Method

The sol-gel method has emerged as a prominent technique for synthesizing bismuth ferrite composites, particularly due to its ability to produce materials with high purity and uniformity at relatively low temperatures [18, 19]. The sol-gel process involves the transition of a solution (sol) into a solid (gel) phase, which is then subjected to heat treatment to achieve crystallization.

Fig. 2 displays the FESEM micrographs of the BiFeO₃ - GdFeO₃ nanocomposites. The white granular particles, visible among the BiFeO₃, represent GdFeO₃, while the quasi-spherical shapes indicate the presence of BiFeO₃ in the nanohybrid structure. The coexistence of these hybrid phases within the same field of view confirms the successful synthesis of BiFeO₃ - GdFeO₃ nanohybrids via the sol-gel method [20]. The primary advantage of this method lies in its ability to control the stoichiometry and morphology of the resulting materials. As shown in Fig. 3, pure BiFeO₃ (BFO) and BiFe_{1-x}Co_xO₃ (BFC_xO, where x = 0.01, 0.03, 0.05, 0.07, and 0.10) composite thin films were fabricated on Si substrates using the sol-gel technique. High-purity bismuth

nitrate, ferric nitrate, and cobalt (II) nitrate hexahydrate were used as starting materials, mixed with ethylene glycol to create a homogeneous precursor solution of 0.2 mol/L after aging for 24 hours. This solution was applied to an impurity-free silicon substrate via spin-casting, which involved two steps: spinning at 500 rpm for 3 seconds and then at 4000 rpm for 20 seconds.




Fig. 2. FESEM micrographs of the BiFeO₃ - GdFeO₃ nanocomposites via the sol-gel method [20].

The wet films were pre-annealed at 350 °C for 6 minutes, and this process was repeated to achieve a semi-finished film of moderate thickness. Finally, the samples were crystallized in air at 500 °C for 1 hour and cooled to room temperature to obtain high-quality thin films [21]. Moreover, William et al. [22] emphasized that the sol-gel method allows for a uniform distribution of nanosized particles, which is critical for achieving the desired multiferroic properties of BiFeO₃. Moreover, the synthesis temperature can be significantly lower than that required for conventional solid-state methods, typically ranging from 300°C to 500°C [23]. This reduction in temperature not only saves energy but also minimizes the risk of secondary phase formation, which can compromise the material's properties [15]. In the sol-gel synthesis of BiFeO₃, various precursors such as bismuth nitrate and iron nitrate are commonly used. The choice of solvent and the presence of complexing agents can significantly influence the final product's characteristics. For example, Liu et al. [24] demonstrated that using polyvinyl alcohol (PVA) as a stabilizing agent during the sol-gel process resulted in improved crystallinity and reduced impurity levels in the synthesized BiFeO₃. Similarly, the incorporation of chelating agents like glycine has been shown to enhance the purity and phase homogeneity of BiFeO₃, as reported by Wahba et al. [25]. The properties of BiFeO₃ synthesized via the sol-gel method are often superior to those produced by other techniques. For instance, Yi et al. [26] highlighted that sol-gel-derived BiFeO₃ films exhibit outstanding ferroelectric properties, with large polarization values that are crucial for applications in memory devices and sensors. Additionally, the ability to tailor the microstructure through sol-gel processing allows for the optimization of electrical and magnetic properties, making it a versatile approach for developing advanced materials. However, challenges remain in achieving phase-pure BiFeO₃, as secondary phases such as bismuth oxide can form during the synthesis and subsequent calcination processes [27]. Zhang et al. [28] noted that careful control of the synthesis parameters, including temperature and precursor concentrations, is essential to mitigate these issues and enhance the purity of the final product.




Fig. 3. A thin film preparation process for pure BiFeO₃ (BFO) and BiFe_{1-x}Co_xO₃ composites [21].

2.2. Hydrothermal Synthesis

Hydrothermal synthesis is a versatile method that allows for the controlled fabrication of BiFeO₃ with desired morphologies and sizes. The process typically involves the reaction of bismuth and iron precursors in an aqueous solution at elevated temperatures and pressures [11, 29]. For instance, Chen et al. [30] demonstrated that the use of a sol-gel-hydrothermal method could yield bismuth ferrite microcrystals at low temperatures, emphasizing the importance of optimizing precursor concentrations to achieve pure-phase BiFeO₃. Similarly, Li et al. [31] highlighted the role of polyethylene glycol (PEG) in controlling the morphology of BiFeO₃ microcrystals, resulting in uniform structures beneficial for various applications. The ability to manipulate the synthesis parameters, such as temperature and precursor concentration, is crucial for tailoring the properties of BiFeO₃ composites.

The structural integrity and phase purity of BiFeO₃ synthesized via hydrothermal methods have been extensively characterized. For example, Sun et al. [32] reported that BiFeO₃ nanoflakes produced through hydrothermal synthesis exhibited sharp X-ray diffraction (XRD) peaks corresponding to the pure phase of BiFeO₃, confirming the effectiveness of the hydrothermal method in achieving high crystallinity. Furthermore, the introduction of external factors, such as magnetic fields during synthesis, has been shown to influence the morphology and magnetic properties of BiFeO₃, leading to enhanced performance in applications such as magnetic sensors [33]. This highlights the potential of hydrothermal synthesis not only for producing high-quality materials but also for engineering their properties through external conditions. The photocatalytic properties of BiFeO₃ composites have also been a focal point of research. The incorporation of materials such as graphene or gold nanoparticles into BiFeO₃ has been explored to enhance its photocatalytic efficiency. For instance, Dai et al. [34] successfully synthesized BiFeO₃-graphene composites using hydrothermal methods, demonstrating improved photocatalytic activities due to the synergistic effects of the two materials. Additionally, the decoration of BiFeO₃ with Ag nanoparticles has been shown to retain its intrinsic magnetic properties while enhancing photocatalytic performance, making it a promising candidate for environmental remediation applications [35]. Abdalla S. Abdelhamid et al. [36] investigated the synthesis of a BiOF/BiFeO₃ hybrid heterojunction for photocatalytic applications. As shown in Fig.4 composite was synthesized hydrothermally and showed

effective photocatalytic activity for the aerobic oxidation of benzylamine under simulated light. The results indicated a high conversion yield of approximately 80%, demonstrating the enhanced performance of the composite in this reaction.

2.3. Solid-State Reaction

The solid-state reaction method is one of the oldest techniques for synthesizing BiFeO₃ but often suffers from issues related to phase purity and particle size control [37, 38]. Recent studies have focused on optimizing various parameters to enhance the quality of BiFeO₃ synthesized via solid-state reactions [39, 40].




Fig. 4. Synthesizing BiFeO₃, BiOF, and BiOF/BiFeO₃ composite materials using hydrothermal methods [36].

The research by Tuluk et al. [37] indicates that adjusting calcination and sintering temperatures can significantly impact phase purity. For example, a study found that a calcination temperature of 750 °C followed by sintering at

775 °C produced high-density ceramics with minimal secondary phases. Incorporating mechanical activation before sintering has been shown to lower the formation temperature of the perovskite phase by approximately 100 °C. This approach enhances diffusion rates and promotes more uniform particle sizes, leading to improved magnetic and ferroelectric properties [41]. A novel technique called reaction flash-sintering has emerged as a promising alternative, allowing for rapid densification at lower temperatures. This method involves applying an electric field during sintering, which can lead to dense nanostructured polycrystals of BiFeO₃ in a matter of seconds [42].

2.4. Other Techniques for Synthesizing BiFeO₃ Composites

In addition to the more traditional methods such as solid-state reaction, sol-gel, and hydrothermal synthesis, several other innovative techniques have emerged for synthesizing BiFeO₃ composites. These methods often provide unique advantages in terms of control over morphology, particle size, and phase purity. Sonochemical synthesis is a technique that utilizes ultrasonic waves to promote chemical reactions in a solution [29]. This method has gained popularity for synthesizing BiFeO₃ composites due to its ability to enhance reaction kinetics and produce fine nanoparticles with controlled properties. In sonochemical synthesis, metal precursors (e.g., bismuth nitrate and iron nitrate) are dissolved in a solvent, typically water [43]. The solution is then subjected to ultrasonic irradiation, which generates cavitation bubbles that collapse violently, producing localized high temperatures and pressures. This environment facilitates the rapid formation of nanoparticles through nucleation and growth processes [44]. S. Das et al. [45] have reported for the first time that phase-pure BiFeO₃, synthesized via a sonochemical method, exhibits remarkable sensitivity in detecting low concentrations of SO₂, along with impressive response and recovery times. In contrast, BiFeO₃ produced through traditional precipitation methods, which do not involve sonication, contains impurity phases and fails to demonstrate similar SO₂ sensing capabilities.

3. Applications of BiFeO₃ Composites

BiFeO₃ composites are renowned for their unique combination of ferroelectric, magnetic, and optical properties. These characteristics make them suitable for a wide range of applications across various fields. The ability to tailor their properties through doping and composite formation enhances their functionality, leading to innovative uses in technology and industry [46, 47]. As one of the most promising technologies for environmental purification and solar energy conversion, semiconductor photocatalysis has gained considerable interest in recent years. Exploration of visible-light-driven photocatalysts is a hotspot of activity in the photocatalysis field [48]. Jiquan Li et al. [49] synthesized bismuth ferrite (BiFeO₃, BFO) submicron cubes and 3D BFO/graphene composites via a hydrothermal method. The

3D composites exhibited significantly enhanced photocatalytic activity, achieving a 92% degradation rate of methylene blue (MB) at a graphene oxide concentration of 3 mg/mL in 140 minutes. This improvement is due to their large specific surface area and 3D architecture, which enhance charge separation. The photocatalytic mechanism of the 3D BFO/graphene composite is illustrated in Fig. 5. Banoth et al. [50] explored the photocatalytic potential of BiFeO₃ (BFO)-Fe₂O₃ composites for the degradation of methylene blue (MB) dye under sunlight. Using a microwave-assisted coprecipitation method, they synthesized composites with different ratios of Fe₂O₃ (10%, 20%, and 30%) into BiFeO₃, named BFOF10, BFOF20, and BFOF30, respectively. This study revealed that the composites exhibited enhanced photocatalytic activity compared to pure BiFeO₃ due to improved visible light absorption and reduced electron-hole recombination. Notably, BFOF30 achieved a remarkable 94% degradation efficiency of MB under sunlight. This enhancement was attributed to the narrowed band gaps and improved microstructural characteristics, which facilitated efficient charge separation at the BFO-Fe₂O₃ interface. Additionally, the magnetic properties of the composites allowed for their easy recovery and reuse without structural degradation, as confirmed by XRD analysis post-photocatalysis [50]. Khikhlovskiy [51] highlighted that BiFeO₃ is one of the most promising multiferroic materials due to its coupled ferroelectric and antiferromagnetic properties at room temperature. They emphasized that while bulk BiFeO₃ exhibits weak magnetoelectric coupling, significant advancements have been made in thin-film heterostructures. These findings underscore the potential of nanoscale engineering in improving the functional properties of BiFeO₃ for advanced applications [52]. Heng Wu et al. [53] reviewed the fabrication and characterization of low-dimensional BiFeO₃ nanostructures, focusing on their unique properties and applications. They noted that nanostructured BiFeO₃ exhibits enhanced ferroelectricity, magnetism, and photocatalytic activity compared to its bulk counterpart. The review emphasized that controlling particle size and morphology through advanced synthesis techniques such as hydrothermal synthesis and sol-gel methods can significantly influence the material's performance in applications like energy harvesting, sensors, and environmental remediation. Similarly, Nan Wang et al. [54] discussed the structural performance and application potential of BiFeO₃ nanomaterials in their study. They highlighted that doping strategies and composite formation are effective approaches to enhance the photocatalytic efficiency and magnetic properties of BiFeO₃. The integration of BiFeO₃ with other materials in heterostructures has shown promise in improving charge separation and reducing recombination rates, making it suitable for applications in photocatalysis and spintronics. These studies collectively demonstrate that recent advances in synthesis methods, such as microwave-assisted coprecipitation and heterostructure engineering, have significantly enhanced the functional properties of BiFeO₃ composites.

These improvements open new avenues for other applications in energy harvesting, environmental remediation, and multifunctional devices. Recent literature highlights the versatility of BiFeO₃ due to its unique properties, which

include a narrow band gap and strong photocatalytic activity under visible light irradiation. The efficiency of dye degradation is influenced by several factors, including the synthesis method, which can affect the structural and electronic properties of the photocatalyst [2, 14, 55, 56]. In this context, various synthesis techniques such as sol-gel [57], hydrothermal [11], and co-precipitation [58] methods have photocatalytic properties, making them more effective for environmental remediation applications. This review underscores the importance of optimizing synthesis methods to enhance the performance of BiFeO₃ composites in dye degradation, thereby contributing to advancements in photocatalytic technology for wastewater treatment.




Fig. 5. A diagram of photocatalysis mechanism 3D BFO/graphene composite [49].

been employed to produce BiFeO₃ composites with enhanced photocatalytic performance. The comparative analysis presented in this study, as shown in Table 1, illustrates the differences in dye degradation rates among these composites. The results indicate that certain synthesis methods yield BiFeO₃ composites with superior

4. Future Directions for BiFeO₃ Composites

Recent progress in BiFeO₃ composites offers many opportunities for future research and development. Its unique multiferroic properties make BiFeO₃ a promising candidate for various technological applications. Research by Wang et al. emphasizes the significance of BiFeO₃-based heterostructures in advancing the material's properties and applications. Future studies should focus on optimizing the interfaces within these heterostructures to maximize performance in applications like data storage and energy conversion [11, 58].

The exploration of flexible substrates for BiFeO₃ thin films represents a promising direction for future research. Further research should investigate the mechanical properties and long-term stability of these flexible devices to ensure their viability in real-world applications such as wearable electronics and flexible sensors. Doping BiFeO₃ with various ions has shown the potential in improving its functional properties [59]. Wu et al.[53] highlighted that low-dimensional BiFeO₃ nanostructures exhibit size-dependent properties that can be further enhanced through strategic doping. Future work should explore a broader range of dopants and their effects on the electrical, magnetic, and optical properties of BiFeO₃ composites, aiming to tailor materials for specific applications.

Table 1

Comparative study of the dye degradation efficiencies of various BiFeO₃ composite photocatalyst with different synthesis.

Composite	Synthesis	Degradation Efficiency	Reaction condition	Dye used	Ref.
BiFeO ₃ /MOF	One-pot hydrothermal	48%	Visible light irradiation using a 300 W Xe lamp in a catalytic reactor at 20 °C	Methylene Blue (MB)	[60]
BiFeO ₃ /GdFeO ₃	Sol-gel	56%	Natural sunlight and at atmospheric temperature/	Methylene Blue (MB)	[61]
BiFeO ₃ /ZnO	Hydrothermal method	-	Ultrasonic: 158 W, 40 kHz UV-vis light: 200–800 nm	RhB (11.2) MB (30.4) MO (19.3)	[62]
Bi ₂ S ₃ /BiFeO ₃	Hydrothermal route	96%	under visible-light irradiation	Rhodamine B (RhB)	[63]

BiFeO ₃ /ZnFe ₂ O ₄	Hydrothermal method.	-	under visible light irradiation	Tetracycline (1.63) and methylene blue (1.38)	[64]
BiFeO ₃ /CdS (9)/rGO	Hydrothermal method	96%,92%	visible light irradiation	Methylene Blue (MB) Methyl orange (MO)	[65]
Ag/AgCl/Bi ₂ O ₃ /BiFeO ₃	Simple co-precipitation and sono-chemical	-	-	-	[66]
BiFeO ₃ /rGO	Sol-gel	98%	visible-light	Methylene Blue (MB)	[67]
SnO ₂ /BiFeO ₃	Sol-gel synthesis	87.2% of RhB and 65.1% of 2,4-DCP	under the visible light irradiation,	2,4-DCP and RhB	[57]
BiFeO ₃ – TiO ₂	Hydrothermal	70%	under visible-light irradiation	-	[68]
Bi ₂ O ₃ /BiFeO ₃ p-n	In-situ growth	Photodegradation rate was 8.7 and 5.4	under visible light irradiation	Tetracycline hydrochloride (TC)	[69]
Ag ₂ S/BiFeO ₃	Precipitation method	~70% and ~84%	under Visible-Light Irradiation	Methyl orange (MO)	[70]
BiFeO ₃ -g-C ₃ N ₄ -WO ₃ Z-scheme	wet chemical method	63%	visible light	2,4-DCP degradation	[55]
Bi ₂ MoO ₆ /BiFeO ₃	Solvothermal process	82%, 98% and 93%	visible-light	Rhodamine B (RhB) and tetracycline hydrochloride (TC)	[56]
Z-scheme Ag/FeTiO ₃ /Ag/BiFeO ₃	Sol-gel method	96.5%	under visible light irradiation	hydroxyl radicals (radical. OH), holes (h ⁺) and superoxide radicals (radical .O ₂ ⁻)	[71]
BiFeO ₃ /CuBi ₂ O ₄ /BaTiO	The isoelectric point-assisted calcination method	93.5 %	V-vis and near-infrared (NIR) light,	Norflloxacin (NFX)	[72]

5. Conclusion

Recent advances in synthesizing BiFeO₃ composites highlight challenges and opportunities in this field. While issues related to phase purity, microstructural control, and scalability persist, innovative approaches such as doping strategies, heterostructure, and advanced characterization techniques offer pathways toward enhancing material performance. Continued research will be essential for unlocking the full potential of BiFeO₃ composites in various technological applications.

Author's contribution

Marzieh fattahi: Writing – original draft, Validation, Writing– review & editing, Methodology, Investigation.

Funding

No funding was received for this work.

Declaration of competing interest

The author has no conflicts of interest to disclose.

Data availability

No data was used for the research described in the article.

REFERENCES

- [1] C. Gumiel, D.G. Calatayud, Thin film processing of multiferroic BiFeO₃: From sophistication to simplicity. A review, *Boletín de la Sociedad Española de Cerámica y Vidrio* 61(6) (2022) 708-732.
- [2] C. Gumiel, T. Vranken, M.S. Bernardo, T. Jardiell, A. Hardy, M.K. Van Bael, M. Peiteado, Thin film composites in the BiFeO₃-Bi₄Ti₃O₁₂ system obtained by an aqueous solution-gel deposition methodology, *Boletín de la Sociedad Española de Cerámica y Vidrio* 57(1) (2018) 19-28.
- [3] N. Itoh, T. Shimura, W. Sakamoto, T. Yogo, Fabrication and Characterization of BiFeO₃-BaTiO₃ Ceramics by Solid State Reaction, *Ferroelectrics* 356(1) (2007) 19-23.
- [4] T. Cadenbach, M.J. Benitez, A.L. Morales, C. Costa Vera, L. Lascano, F. Quiroz, A. Debut, K. Vizuete, Nanocasting synthesis of BiFeO₃ nanoparticles with enhanced visible-light photocatalytic activity, *Beilstein Journal of Nanotechnology* 11 (2020) 1822-1833.
- [5] Q. Li, S. Bao, T. Hong, L. Ai, Y. Liu, Y. Jing, J. Li, Influence of Vanadium Substitution on Phase Structure, Magnetic and Dielectric Properties of BiFeO₃ Ceramics, *Journal of Magnetism* 23(1) (2018) 5-10.
- [6] T. Soltani, B.-K. Lee, Sono-synthesis of nanocrystallized BiFeO₃/reduced graphene oxide composites for visible photocatalytic degradation

- improvement of bisphenol A, *Chemical Engineering Journal* 306 (2016) 204-213.
- [7] T. Zhang, Y. Shen, Y. Qiu, Y. Liu, R. Xiong, J. Shi, J. Wei, Facial Synthesis and Photoreaction Mechanism of BiFeO₃/Bi₂Fe₄O₉ Heterojunction Nanofibers, *ACS Sustainable Chemistry & Engineering* 5(6) (2017) 4630-4636.
- [8] T. Fan, C. Chen, Z. Tang, Hydrothermal synthesis of novel BiFeO₃/BiVO₄ heterojunctions with enhanced photocatalytic activities under visible light irradiation, *RSC Advances* 6(12) (2016) 9994-10000.
- [9] R. Safi, H. Shokrollahi, Physics, chemistry and synthesis methods of nanostructured bismuth ferrite (BiFeO₃) as a ferroelectro-magnetic material, *Progress in Solid State Chemistry* 40(1) (2012) 6-15.
- [10] M. Bernardo, Synthesis, microstructure and properties of BiFeO₃, *Boletín de la Sociedad Española de Física* 1 (2014).
- [11] S. Li, Synthesis and Functional Properties Of BiFeO₃ And BiFeCrO₆ Based Nanostructures and Thin Films, Institut National de la Recherche Scientifique (Canada), 2014.
- [12] Z. Hu, D. Chen, S. Wang, N. Zhang, L. Qin, Y. Huang, Facile synthesis of Sm-doped BiFeO₃ nanoparticles for enhanced visible light photocatalytic performance, *Materials Science and Engineering: B* 220 (2017) 1-12.
- [13] Y. Zhang, Y. Wang, J. Qi, Y. Tian, M. Sun, J. Zhang, T. Hu, M. Wei, Y. Liu, J. Yang, Enhanced Magnetic Properties of BiFeO₃ Thin Films by Doping: Analysis of Structure and Morphology, *Nanomaterials*, 2018.
- [14] R. Zhang, S. Liu, F. Kong, J. Tong, L. Ruan, Q. Duan, J. Zhou, X. Zhang, α -Fe₂O₃/BiFeO₃ composites as visible-active photocatalysts and their optical response mechanism, *Journal of Physics and Chemistry of Solids* 141 (2020) 109329.
- [15] N.R. Niloy, M. Chowdhury, S. Anwar, J. Islam, M. Rhaman, Structural and optical characterization of multiferroic bifeo₃ nanoparticles synthesized at different annealing temperatures, (2020).
- [16] L. Yin, W. Mi, Progress in BiFeO₃-based heterostructures: materials, properties and applications, *Nanoscale* 12(2) (2020) 477-523.
- [17] S. Ramazanov, D. Sobola, F. Orudzhev, A. Knápek, J. Polčák, M. Potoček, P. Kaspar, R. Dallaev, Surface Modification and Enhancement of Ferromagnetism in BiFeO₃ Nanofilms Deposited on HOPG, *Nanomaterials*, 2020.
- [18] A. Nageena, A. Manzoor, A.M. Afzal, M.I. Arshad, A. Shahzad, M. Kashif, Investigation of dielectric, magnetic and electrical behavior of BFO/GNPs nano-composites synthesized via sol-gel method, *Journal of Materials and Physical Sciences* 3(2) (2022) 59-70.
- [19] M. Zahid, N. Nadeem, M.A. Hanif, I.A. Bhatti, H.N. Bhatti, G. Mustafa, Metal Ferrites and Their Graphene-Based Nanocomposites: Synthesis, Characterization, and Applications in Wastewater Treatment, in: K.A. Abd-Elsalam, M.A. Mohamed, R. Prasad (Eds.), *Magnetic Nanostructures : Environmental and Agricultural Applications*, Springer International Publishing, Cham, 2019, pp. 181-212.
- [20] Y. Subramanian, V. Ramasamy, R.J. Karthikeyan, G.R. Srinivasan, D. Arulmozhi, R.K. Gubendiran, M. Sriramulu, Investigations on the enhanced dye degradation activity of heterogeneous BiFeO₃-GdFeO₃ nanocomposite photocatalyst, *Heliyon* 5(6) (2019).
- [21] L. Bai, M. Sun, W. Ma, J. Yang, J. Zhang, Y. Liu, Enhanced Magnetic Properties of Co-Doped BiFeO₃ Thin Films via Structural Progression, *Nanomaterials*, 2020.
- [22] R.V. William, A. Marikani, K. Gangatharan, Investigation of Multiferroic BiFeO₃ Nanorods Using 2-MOE(C₃H₈O₂)-Assisted Citrate Sol-Gel Method, *International Journal of Nanoscience* 18(05) (2018) 1850029.
- [23] H. Ke, W. Wang, Y. Wang, J. Xu, D. Jia, Z. Lu, Y. Zhou, Factors controlling pure-phase multiferroic BiFeO₃ powders synthesized by chemical co-precipitation, *Journal of Alloys and Compounds* 509(5) (2011) 2192-2197.
- [24] T.-y. Liu, Y. Xu, J. Zhao, Low-Temperature Synthesis of BiFeO₃ via PVA Sol-Gel Route, *Journal of the American Ceramic Society* 93 (2010) 3637-3641.
- [25] M.A. Wahba, S.M. Yakout, A.M. Youssef, W. Sharmoukh, A.M.E. Sayed, M.S. Khalil, Chelating Agents Assisted Rapid Synthesis of High Purity BiFeO₃: Remarkable Optical, Electrical, and Magnetic Characteristics, *Journal of Superconductivity and Novel Magnetism* 35(12) (2022) 3689-3704.
- [26] J. Yi, L. Liu, L. Shu, Y. Huang, J.F. Li, Outstanding Ferroelectricity in Sol-Gel-Derived Polycrystalline BiFeO₃ Films within a Wide Thickness Range, *ACS Appl Mater Interfaces* 14(18) (2022) 21696-21704.
- [27] J.L. Ortiz-Quiñonez, D. Diaz, I. Zumeta-Dubé, H. Arriola-Santamaría, I. Betancourt, P. Santiago-Jacinto, N. Nava-Etzana, Easy Synthesis of High-Purity BiFeO₃ Nanoparticles: New Insights Derived from the Structural, Optical, and Magnetic Characterization, *Inorganic Chemistry* 52(18) (2013) 10306-10317.
- [28] Y. Zhang, B. Li, Y. Jia, High Humidity Response of Sol-Gel-Synthesized BiFeO₃ Ferroelectric Film, *Materials*, 2022.
- [29] C. Zhao, H. Zhang, X. Cheng, Spectroscopic study on the valence state of Fe in BiFeO₃, *Journal of Solid State Chemistry* 311 (2022) 123145.
- [30] Z. Chen, G. Zhan, X. He, H. Yang, H. Wu, Low-temperature preparation of bismuth ferrite microcrystals by a sol-gel-hydrothermal method, *Crystal Research and Technology* 46(3) (2011) 309-314.
- [31] S. Li, Y.-H. Lin, B.-P. Zhang, Y. Wang, C.-W. Nan, Controlled Fabrication of BiFeO₃ Uniform Microcrystals and Their Magnetic and Photocatalytic Behaviors, *The Journal of Physical Chemistry C* 114(7) (2010) 2903-2908.
- [32] B. Sun, S. Mao, S. Zhu, G. Zhou, Y. Xia, Y. Zhao, Improved Rate and Cycling Performances of Electrodes Based on BiFeO₃ Nanoflakes by Compositing with Organic Pectin for Advanced Rechargeable Na-Ion Batteries, *ACS Applied Nano Materials* 1(3) (2018) 1291-1299.
- [33] L. Hou, K. Zuo, Q. Sun, Z. Ren, Y. Zeng, X. Li, Effects of external magnetic field on the morphology and magnetic property of BiFeO₃ particles prepared by hydrothermal synthesis, *Applied Physics Letters* 102(8) (2013).
- [34] J.F. Dai, T. Xian, L.J. Di, H. Yang, Preparation of BiFeO₃-Graphene Nanocomposites and Their Enhanced Photocatalytic Activities, *Journal of Nanomaterials* 2013(1) (2013) 642897.
- [35] Navjot, A. Tovstolytkin, G.S. Lotey, Plasmonic Enhanced Photocatalytic Activity of Ag Nanospheres Decorated BiFeO₃ Nanoparticles, *Catalysis Letters* 147(7) (2017) 1640-1645.
- [36] A.S. Abdelhamid, R.H. Alzard, L.A. Siddig, A. Elbahnasy, D. Aljazmati, Z. Kadoura, H. Zeidane, R. Elshikh, A. Alzamy, Facile Synthesis, Characterization, and Photocatalytic Performance of BiOF/BiFeO₃ Hybrid Heterojunction for Benzylamine Coupling under Simulated Light Irradiation, *Photochem*, 2023, pp. 187-196.
- [37] A.Y. Tuluk, T.R. Mahon, S.v.d. Zwaag, P. Groen, BiFeO₃ synthesis by conventional solid-state reaction, 2019 IEEE International Symposium on Applications of Ferroelectrics (ISAF), 2019, pp. 1-4.
- [38] M. Valant, A.-K. Axelsson, N. Alford, Peculiarities of a Solid-State Synthesis of Multiferroic Polycrystalline BiFeO₃, *Chemistry of Materials* 19(22) (2007) 5431-5436.
- [39] M.K. Sharif, M.A. Khan, A. Hussain, F. Iqbal, I. Shakir, G. Murtaza, M.N. Akhtar, M. Ahmad, M.F. Warsi, Synthesis and characterization of Zr and Mg doped BiFeO₃ nanocrystalline multiferroics via micro emulsion route, *Journal of Alloys and Compounds* 667 (2016) 329-340.
- [40] R.K. Upadhyay, A.P. Singh, D. Upadhyay, A. Kumar, C. Kumar, S. Jit, BiFeO₃/CH₃NH₃PbI₃ Perovskite Heterojunction Based Near-Infrared Photodetector, *IEEE Electron Device Letters* 40(12) (2019) 1961-1964.
- [41] H. Han, J.H. Lee, H.M. Jang, Low-Temperature Solid-State Synthesis of High-Purity BiFeO₃ Ceramic for Ferroic Thin-Film Deposition, *Inorganic Chemistry* 56(19) (2017) 11911-11916.
- [42] E. Gil-González, A. Perejón, P.E. Sánchez-Jiménez, M.J. Sayagués, R. Raj, L.A. Pérez-Maqueda, Phase-pure BiFeO₃ produced by reaction flash-sintering of Bi₂O₃ and Fe₂O₃, *Journal of Materials Chemistry A* 6(13) (2018) 5356-5366.
- [43] L. Fei, Chemical synthesis and characterization of bismuth ferrite nanostructures, (2011).
- [44] R.L. Palomino-Resendiz, A.M. Bolarín-Miró, F. Pedro-García, F. Sánchez-De Jesús, J.P. Espinós-Manzorro, C.A. Cortés-Escobedo, Analysis of the effect of cationic ratio Bi³⁺/Fe³⁺ on the magnetic and multiferroic properties of BiFeO₃ nanoparticles synthesized using a sonochemical-assisted method, *Ceramics International* 48(10) (2022) 14746-14753.
- [45] S. Das, S. Rana, S.M. Mursalin, P. Rana, A. Sen, Sonochemically prepared nanosized BiFeO₃ as novel SO₂ sensor, *Sensors and Actuators B: Chemical* 218 (2015) 122-127.
- [46] A. Das, S. De, S. Bandyopadhyay, S. Chatterjee, D. Das, Magnetic, dielectric and magnetoelectric properties of BiFeO₃-CoFe₂O₄ nanocomposites, *Journal of Alloys and Compounds* 697 (2017) 353-360.
- [47] J. Silva, A. Reyes, H. Esparza, H. Camacho, L. Fuentes, BiFeO₃: A Review on Synthesis, Doping and Crystal Structure, *Integrated Ferroelectrics* 126(1) (2011) 47-59.
- [48] L. Di, H. Yang, T. Xian, X. Chen, Construction of Z-Scheme g-C₃N₄/CNT/Bi₂Fe₄O₉ Composites with Improved Simulated-Sunlight Photocatalytic Activity for the Dye Degradation, *Micromachines*, 2018.
- [49] J. Li, Y. Wang, H. Ling, Y. Qiu, J. Lou, X. Hou, S.P. Bag, J. Wang, H. Wu, G. Chai, Significant Enhancement of the Visible Light Photocatalytic Properties in 3D BiFeO₃/Graphene Composites, *Nanomaterials*, 2019.
- [50] P. Banoth, B.P. Narsaiah, L. De Los Santos Valladares, J. Kargin, P. Kollu, Single-phase BiFeO₃ and BiFeO₃-Fe₂O₃ nanocomposite photocatalysts for photodegradation of organic dye pollutants, *Nanoscale Advances* 5(9) (2023) 2646-2656.
- [51] S.V.V. Khikhlovskiy, G. Blake, The renaissance of multiferroics: bismuth ferrite (BiFeO₃)—a candidate multiferroic material in nanoscience, *University of Groningen* 1(3) (2010).
- [52] I. Calisir, A.A. Amirov, A.K. Kleppe, D.A. Hall, Optimisation of functional properties in lead-free BiFeO₃-BaTiO₃ ceramics through La³⁺ substitution strategy, *Journal of Materials Chemistry A* 6(13) (2018) 5378-5397.

- [53] H. Wu, J. Zhou, L. Liang, L. Li, X. Zhu, Fabrication, Characterization, Properties, and Applications of Low-Dimensional BiFeO₃ Nanostructures, *Journal of Nanomaterials* 2014(1) (2014) 471485.
- [54] N. Wang, X. Luo, L. Han, Z. Zhang, R. Zhang, H. Olin, Y. Yang, Structure, Performance, and Application of BiFeO₃ Nanomaterials, *Nano-Micro Letters* 12(1) (2020) 81.
- [55] S. Ali, M. Humayun, W. Pi, Y. Yuan, M. Wang, A. Khan, P. Yue, L. Shu, Z. Zheng, Q. Fu, W. Luo, Fabrication of BiFeO₃-g-C₃N₄-WO₃ Z-scheme heterojunction as highly efficient visible-light photocatalyst for water reduction and 2,4-dichlorophenol degradation: Insight mechanism, *Journal of Hazardous Materials* 397 (2020) 122708.
- [56] R. Tao, C. Shao, X. Li, X. Li, S. Liu, S. Yang, C. Zhao, Y. Liu, Bi₂MoO₆/BiFeO₃ heterojunction nanofibers: Enhanced photocatalytic activity, charge separation mechanism and magnetic separability, *Journal of Colloid and Interface Science* 529 (2018) 404-414.
- [57] M.A. Marwat, H. Ullah, M. Usman, M.A. Ehsan, H. Zhang, M.F. Khan, S. Ali, M. Yousaf, Significantly improved photocatalytic activity of the SnO₂/BiFeO₃ heterojunction for pollutant degradation and mechanism, *Ceramics International* 48(10) (2022) 14789-14798.
- [58] I.Y. Khairani, A.N. Arifiadi, J.-H. Lee, B. Bhoi, S.K.S. Patel, S.-k. Kim, Fabrication, structure, and magnetic properties of pure-phase BiFeO₃ and MnFe₂O₄ nanoparticles and their nanocomposites, *J. Magn* 25(2) (2020) 140-149.
- [59] B. Jana, K. Ghosh, K. Rudrapal, P. Gaur, P. Shihabudeen, A. Roy Chaudhuri, Recent progress in flexible multiferroics, *Frontiers in Physics* 9 (2022) 822005.
- [60] Y. Si, Y. Li, J. Zou, X. Xiong, X. Zeng, J. Zhou, Photocatalytic Performance of a Novel MOF/BiFeO₃ Composite, *Materials*, 2017.
- [61] Y. Subramanian, V. Ramasamy, R.J. Karthikeyan, G.R. Srinivasan, D. Arulmozhi, R.K. Gubendiran, M. Sriramalu, Investigations on the enhanced dye degradation activity of heterogeneous BiFeO₃-GdFeO₃ nanocomposite photocatalyst, *Heliyon* 5(6) (2019) e01831.
- [62] T.N. Nhan Nguyen, K.-S. Chang, Piezoelectricity-enhanced multifunctional applications of hydrothermally-grown p-BiFeO₃-n-ZnO heterojunction films, *Renewable Energy* 197 (2022) 89-100.
- [63] Y.P. Bhoi, A.K. Nayak, S.K. Gouda, B.G. Mishra, Photocatalytic mineralization of carbendazim pesticide by a visible light active novel type-II Bi₂S₃/BiFeO₃ heterojunction photocatalyst, *Catalysis Communications* 114 (2018) 114-119.
- [64] X. Jiang, Z. Wang, M. Zhang, M. Wang, R. Wu, X. Shi, B. Luo, D. Zhang, X. Pu, H. Li, A novel direct Z-scheme heterojunction BiFeO₃/ZnFe₂O₄ photocatalyst for enhanced photocatalyst degradation activity under visible light irradiation, *Journal of Alloys and Compounds* 912 (2022) 165185.
- [65] H. Alijani, M. Abdouss, H. Khataei, Efficient photocatalytic degradation of toxic dyes over BiFeO₃/CdS/rGO nanocomposite under visible light irradiation, *Diamond and Related Materials* 122 (2022) 108817.
- [66] Y. Li, W. Yin, M. Li, J. Zhang, L. Chen, Multi-component Ag/AgCl/Bi₂O₃/BiFeO₃ for the sunlight-induced photocatalytic degradation, *Journal of Environmental Chemical Engineering* 10(2) (2022) 107280.
- [67] M. Ghorbani, S. Sheibani, H. Abdizadeh, M.R. Golobostanfard, Modified BiFeO₃/rGO nanocomposite by controlled synthesis to enhance adsorption and visible-light photocatalytic activity, *Journal of Materials Research and Technology* 22 (2023) 1250-1267.
- [68] S. Li, Y.-H. Lin, B.-P. Zhang, J.-F. Li, C.-W. Nan, BiFeO₃/TiO₂ core-shell structured nanocomposites as visible-active photocatalysts and their optical response mechanism, *Journal of Applied Physics* 105(5) (2009).
- [69] F. Duan, Y. Ma, P. Lv, J. Sheng, S. Lu, H. Zhu, M. Du, X. Chen, M. Chen, Oxygen vacancy-enriched Bi₂O₃/BiFeO₃ p-n heterojunction nanofibers with highly efficient photocatalytic activity under visible light irradiation, *Applied Surface Science* 562 (2021) 150171.
- [70] L. Di, H. Yang, T. Xian, X. Liu, X. Chen, Photocatalytic and Photo-Fenton Catalytic Degradation Activities of Z-Scheme Ag₂S/BiFeO₃ Heterojunction Composites under Visible-Light Irradiation, *Nanomaterials*, 2019.
- [71] J. Tang, R. Wang, M. Liu, Z. Zhang, Y. Song, S. Xue, Z. Zhao, D.D. Dionysiou, Construction of novel Z-scheme Ag/FeTiO₃/Ag/BiFeO₃ photocatalyst with enhanced visible-light-driven photocatalytic performance for degradation of norfloxacin, *Chemical Engineering Journal* 351 (2018) 1056-1066.
- [72] X. Zhang, X. Wang, J. Chai, S. Xue, R. Wang, L. Jiang, J. Wang, Z. Zhang, D.D. Dionysiou, Construction of novel symmetric double Z-scheme BiFeO₃/CuBi₂O₄/BaTiO₃ photocatalyst with enhanced solar-light-driven photocatalytic performance for degradation of norfloxacin, *Applied Catalysis B: Environmental* 272 (2020) 119017.