Available online at www.jourcc.com

Journal homepage: www.JOURCC.com





Journal of Composites and Compounds

Preparation of graphene nanolayers through surfactant-assisted pure shear milling method

Asghar Kazemzadeh^a*, Mohammad Ali Meshkat^b, Houman Kazemzadeh^c, Mostafa Moradi^d, Reza Bahrami^e

Rasul Pouriamanesh^e

^a Department of Semiconductors, Materials and Energy Research Center, Karaj, Iran ^b Department of Nanomaterial, Materials and Energy Research Center, Karaj, Iran ^c Tehran University of Medical Science, Tehran, Iran ^d Department of Materials Science & Engineering, Sharif University of Technology, Tehran, Iran

^e Department of Materials and Metallurgical Engineering, Amirkabir University of Technology, Tehran, Iran

ABSTRACT

In this study, graphite powder was used to prepare few-layer graphene sheets through shear milling. During the Article history: process, graphite was well dispersed in double distilled water as a lubricant and sodium dodecylsulfate (SDS), Received 10 July 2019 followed by shaking and milling under low energy. The exerted sheer force led to the continuous delamination Received in revised form 21 November 2019 of graphene flakes. The microstructural investigation was performed by SEM. In addition, the energy-dispersive Accepted 27 December 2019 X-ray spectroscopy (EDS) analysis was performed to determine distinct levels of carbon in different fragments of graphite. The ultrathin multilayer structure of graphite was successfully obtained using the surfactant of SDS, which can lead to the production of molecularly thin sheets by mechanical peeling. Moreover, it was found that this synthesis method has some advantages, including cost-effectiveness and ease in performance for producing many graphene nanolayers.

©2019 JCC Research Group.

Peer review under responsibility of JCC Research Group.

1. Introduction

These days, nanomaterials, due to their highly attractive properties, have been broadly used in various types of applications, such as life sciences, the environment, information technology, etc. [1-5]. There are various methods to produce nano-sized materials, including sol-gel [6-9], ball-mill [10-13], co-precipitation [5], self-propagating high-temperature synthesis [14, 15], electrospinning [4, 16], etc.

Recently, the application of graphene has been gained increasing attention by researchers because of its unique properties [17-21]. Graphene, a single layer of graphite, is a basic block of sp2-bonded carbon for graphitic materials such as graphite [22-25], fullerene [26-28] and carbon nanotubes [29-38], which has both unique mechanical and physical properties making it a promising material for applications in nanotechnology [39-44]. A stable graphene sheet was discovered by Novoselov and Geim (2004) for the first time [45].

The value of the thermal conductivity of graphene is even more than diamond, and it has a high potential in increasing the convective heat transferring ability of a nanofluid [46-48]. The usage of graphene into the lubricant improves its potential for heat removal from a system, because of the significant role of graphene in increasing the amount of ARTICLE INFORMATION

Keywords: Ultrathin Multilayer Structure Graphene nanolayer Sodium-dodecylsulfate

thermal conductivity. Recently, graphene has been introduced as the thinnest solid lubricant by some researchers with a mechanism of superlubricating, which could be confirmed by atomic force microscopy (AFM) [49, 50]. Graphene has been introduced by Bermen et al. [51], as a promising candidate for using in steel lubricants. The tribological properties of graphene have been investigated, and the results have shown excellent properties of graphene compared to the nanoparticle of graphite or carbon nanotube (CNT) [52].

It can be used in many applications such as solar cells [53, 54], hydrogen storage [7, 55], sensors [56-58], detectors [59], transistors [60] and other electronic devices in many applications due to its good electrical property [19, 21, 61-68], which makes it a good candidate to be used in lots of composites [69, 70]. Therefore, recently, many investigations have been focused on graphene and graphene nanolayer by numerous physicists, chemists, and material scientists [71].

Producing graphene at a large scale with uniform thickness has been one of the most important subjects for many researchers and scientists [72, 73]. Many controlled synthesis routes, viz. chemical vapor deposition (CVD), laser reduction, and wet chemical routes have been proposed to prepare a large amount of graphene [63, 74-78], with suitable physicochemical properties [79-81]. However, these processes should

* Corresponding author: Asghar Kazemzadeh; E-mail: ASG642001@Yahoo.com DOR: 20.1001.1.26765837.2019.1.1.4.3

https://doi.org/10.29252/jcc.1.1.4 This is an open access article under the CC BY license (https://creativecommons.org/licenses/by/4.0)



Fig. 1. Optical microscopy images of graphite particles after 60 hours of shear milling (a) with SDS and (b) without SDS.



Fig. 2. SEM micrographs of graphite particles after 60 hours milling (a) without SDS and (b) with SDS.

be low cost and simple e.g. mechanical exfoliation of graphite, producing a large area graphene sheet.

Several methods have been used for producing layered materials, like graphene, with no unwanted defect or functionalization. Meanwhile, mechanical exfoliation is the best option among these methods that is very simple procedure.

The delamination occurs via applied shear and compressive forces on the particles, in which the shear force should overcome the van der walls force existing between the sheets. Accordingly, there are several reports for preparing graphite nano-sheets or graphene by graphite exfoliation through three roll milling or shear ball milling [77, 82, 83].

However, all these studies have used graphene powders in the form of solid additive, in which the obtained suspension had low stability. Meanwhile, commercial fluids require high stability for a long time [84]. To overcome this limitation, functionalized graphene sheets were prepared e.g., aromatic or long alkyl chain functionalized graphene sheets dispersed in non-polar oil medium [85, 86]. Zhang et al. [87] used polyalphaolefin-9 (PAO) and dispersed oleic acid-modified graphene sheets in it. Although long-term storage stability is not achieved, graphene showed good wear resistance.

One of the major challenges in the graphene research field is how to count the number of atomic layers. Although optical microscopy can show graphene with certain layers on a silicon substrate, it is difficult to identify the number of layers of graphene accurately [62]. Therefore, although there are many reports about graphene nanolayers, insufficient reports have been issued about the preparation of the nanolayers via shear milling procedure.

In order to apply effective exfoliation, the stirred-media bead milling system can be utilized that has more shear forces other than impact one. Peukert et al. [75] used this method to prepare scalable graphene in a water medium along with an ionic surfactant.

Thus, in this paper, the synthesis of nanolayers via shear milling procedure is presented instead of the ball milling process to achieve nanolayer graphene flakes and stable dispersion of graphene in the medium. Scanning electron microscope (SEM) and optical microscopy (OM) were also used to characterize thin flakes on Si substrate. To provide well-dispersed graphite in water, sodium dodecyl sulfate (SDS) was used as the surfactant.

2. Experiment Procedure

High purity graphite powder with an average particle size of 200 μ m and SDS were purchased from Merck Co. (Germany). Two SDS-containing and SDS-free mixtures with 0.25 gr graphite and 200 ml deionized water were separately prepared and a flat alumina disc with 2cm diameter and 4mm thickness was put in the flask of each mixture. The flasks were shaken with orbital flask shaker for 60 hours at a speed of 380 rpm to keep the disc flat. Then, the samples were spin-coated on the Si substrate and dried at 80 °C for 2 h.

Raman spectra analysis was done with SEKI 750 Raman analyzer to investigate the sample in argon ion laser (514.5 nm line). The JEOL 2100 electron microscope was used for TEM analysis of samples on a carbon-coated copper grid. The optical microscopy (OM) and SEM (model: LEO 1450 VP) images of the samples were captured, and data of energy-dispersive EDX (model X-MAX) for different areas were collected.

3. Results and Discussion

Since graphite and graphene flakes are hydrophobic and tend to agglomerate in water, an ionic surfactant like SDS can hinder the coagulation and restacking of particles. The resulting suspension of graphite with SDS is stable in water to carry out the rest of the process. During delamination in the stirring media mill, the transferred energy from the grinding media causes sheets to be fractured, and mostly small fragments of graphite can be present in the ultimate suspension. During milling, SDS is adsorbed on the surface of the particles and creates a strong repulsive force that prevents the agglomeration and restacking of delaminated sheets. The optical microscopy results, which are presented in Fig. 1, show that the particle size of graphite flakes decreased to less than 50 µm in both mixtures, after mechanical treatment for 60 h. Fig. 2 represents the SEM images of graphite fragments on the surface of the silicon substrate. The presence of SDS leads to a significant change in the shape of particles after shear milling for 60 h (Fig. 2). It is worth noting that water allows the graphene planes to slip easily and SDS prevents the agglomeration of the particles and keeps the layers apart from each other. Applying low energy through shear milling of the graphite particles induces shear on graphene layers without causing high crystal defects [63].

As can be seen in Fig. 2(b), the particles obtained after 60 hours of milling have flak-like shape. Fig. 3 illustrates the SEM micrographs of thin flaky graphite. The accurate thicknesses of the thin sheets are difficult to estimate. Three areas are highlighted via arrows on in Fig. 3(a).

Energy-dispersive X-ray analysis (EDX) of point 2 is shown in Fig. 3(b), which contains C, O, and Si as well as a negligible amount of Na element. This proves the presence of carbon and silicon existing in the graphene and substrate, respectively. Fig. 4 shows various intensities of carbon at mentioned areas (Fig. 3(a)) after deposition on a silicon substrate. It is evident that the minimum intensity of C level corresponds to the layer with a minimum contrast (point 1), which refers to the very thin layers of graphene.

The transmission electron microscope (TEM) image of nanolayers is shown in Fig. 4. It can be seen that several dark layers are superimposed on each other. This denotes that several graphene nanolayers are stacked.

In order to distinguish the graphene from graphite and determine the number of layers, Raman spectroscopy was performed. D-band about



Fig. 3. (a) SEM micrographs of thin flaky graphite, (b) EDX spectrum of point 2, and (c) carbon intensity at each point .



Fig. 4. TEM micrograph of graphene nanolayers.

1350 cm⁻¹, G-band about 1580 cm⁻¹ and 2D-band about 2700 cm⁻¹ correspond to graphitic materials. Fig. 4 illustrates the Raman spectra of the materials. The G-band at 1581 and 1573 cm⁻¹, and D-band at 1356 and 1352 cm⁻¹ for graphite and graphene samples, respectively, prove almost the graphitic nature of the samples. In addition, the ordered and increased density of sp2 carbon is clear for the milled sample. It is reported that the 2D symmetry, as well as its full width at half maximum (FWHM), can distinguish the graphene and bulk graphite [88]. Furthermore, the 2720 cm⁻¹ is ascribed to a 2D peak for graphite that depicts the formation of few layers as well as the delamination of a few layers or monolayered graphene.

Besides, a single 2D peak was found in many places in the diluted film. On the other hand, the graphitic nature of the peak was also found in some places. Thus, it can be concluded that both multilayers and single-layered graphene sheets are formed.

4. Conclusions

Multilayer graphene sheets were synthesized by simple surfactant-assisted pure shear milling at ambient temperature. Water and SDS would accelerate the peeling-off process, and the SDS ionic surfactant hinders the agglomeration of graphite flakes. Optical microscopy showed the size reduction caused by mechanical energy. In addition, SEM and TEM images showed that the grinding media transferred enough energy to overcome the Van der Waals forces among the graphene sheets. The thickness of the achieved multilayer graphene sheet was estimated to be nano-sized.



Fig. 5. Raman spectra of dispersion after being processed.

Acknowledgment

The author is grateful to the materials and energy research center for financial support and fellowship.

Conflict of Interest

All authors declare no conflicts of interest in this paper.

REFERENCES

A. Moghanian, F. Sharifianjazi, P. Abachi, E. Sadeghi, H. Jafarikhorami, A. Sedghi, Production and properties of Cu/TiO₂ nano-composites, Journal of Alloys and Compounds 698 (2017) 518-524.

^[2] F. Sharifianjazi, N. Parvin, M. Tahriri, Formation of apatite nano-needles on novel gel derived SiO₂-P₂O₅-CaO-SrO-Ag₂O bioactive glasses, Ceramics Interna-tional 43(17) (2017) 15214-15220.

^[3] M. Radmansouri, E. Bahmani, E. Sarikhani, K. Rahmani, F. Sharifianjazi, M. Irani, Doxorubicin hydrochloride - Loaded electrospun chitosan/cobalt ferrite/ tita-nium oxide nanofibers for hyperthermic tumor cell treatment and controlled drug release, International Journal of Biological Macromolecules 116 (2018) 378-384.

^[4] P. Abasian, M. Radmansouri, M. Habibi Jouybari, M.V. Ghasemi, A. Moham-madi, M. Irani, F.S. Jazi, Incorporation of magnetic NaX zeolite/DOX into the PLA/chitosan nanofibers for sustained release of doxorubicin against carcinoma cells death in vitro, International Journal of Biological Macromolecules 121 (2019) 398-406.

^[5] F.S. Jazi, N. Parvin, M. Tahriri, M. Alizadeh, S. Abedini, M. Alizadeh, The relationship between the synthesis and morphology of SnO₂-Ag₂O nanocomposite, Synthesis and Reactivity in Inorganic, Metal-Organic, and Nano-Metal Chemistry 44(5) (2014) 759-764.

[6] A.R. Rouhani, A.H. Esmaeil-Khanian, F. Davar, S. Hasani, The effect of agarose content on the morphology, phase evolution, and magnetic properties of $CoFe_2O_4$ nanoparticles prepared by sol-gel autocombustion method, International Journal of Applied Ceramic Technology 15(3) (2018) 758-765.

[7] V. Salimian Rizi, F. Sharifianjazi, H. Jafarikhorami, N. Parvin, L. Saei Fard, M. Irani, A. Esmaeilkhanian, Sol–gel derived SnO₂/Ag₂O ceramic nanocomposite for H2 gas sensing applications, Materials Research Express 6(11) (2019) 1150g2. [8] S. Abedini, N. Parvin, P. Ashtari, F. Jazi, Microstructure, strength and CO2separation characteristics of α -alumina supported γ -alumina thin film membrane, Advances in Applied Ceramics 112(1) (2013) 17-22.

[9] F. Sharifianjazi, N. Parvin, M. Tahriri, Synthesis and characteristics of solgel bioactive SiO₂-P₂O₅-CaO-Ag₂O glasses, Journal of Non-Crystalline Solids 476 (2017) 108-113.

[10] M. Alizadeh, F. Sharifianjazi, E. Haghshenasjazi, M. Aghakhani, L. Rajabi, Production of nanosized boron oxide powder by high-energy ball milling, Synthe-sis and Reactivity in Inorganic, Metal-Organic, and Nano-Metal Chemistry 45(1) (2015) 11-14.

[11] E.H. Jazi, R. Esalmi-Farsani, G. Borhani, F.S. Jazi, Synthesis and Character-ization of In Situ $Al-Al_{15}Fe_4-Al_2O_3$ -TiB₂ Nanocomposite Powder by Mechanical Alloying and Subsequent Heat Treatment, Synthesis and Reactivity in Inorganic, Metal-Organic, and Nano-Metal Chemistry 44(2) (2014) 177-184.

[12] A. Esmaeilkhanian, F. Sharifianjazi, A. Abouchenari, A. Rouhani, N. Parvin, M. Irani, Synthesis and Characterization of Natural Nano-hydroxyapatite Derived from Turkey Femur-Bone Waste, Applied Biochemistry and Biotechnology 189(3) (2019) 919-932.

[13] E. Sharifi Sedeh, S. Mirdamadi, F. Sharifianjazi, M. Tahriri, Synthesis and evaluation of mechanical and biological properties of scaffold prepared from Ti and Mg with different volume percent, Synthesis and Reactivity in Inorganic, Met-al-Organic, and Nano-Metal Chemistry 45(7) (2015) 1087-1091.

[14] V. Balouchi, F.S. Jazi, A. Saidi, Developing (W, Ti) C-(Ni, Co) nanocomposite by SHS method, Journal of Ceramic Processing Research 16(5) (2015) 605-608.

[15] A. Masoudian, M. Karbasi, F. SharifianJazi, A. Saidi, Developing Al₂O₃-TiC in-situ nanocomposite by SHS and analyzingtheeffects of Al content and mechanical activation on microstructure, Journal of Ceramic Processing Research 14(4) (2013) 486-491.

[16] M. Radmansouri, E. Bahmani, E. Sarikhani, K. Rahmani, F. Sharifianjazi, M. Irani, Doxorubicin hydrochloride-Loaded electrospun chitosan/cobalt ferrite/ tita-nium oxide nanofibers for hyperthermic tumor cell treatment and controlled drug release, International journal of biological macromolecules 116 (2018) 378-384.

[17] K.S. Novoselov, A. Geim, The rise of graphene, Nat. Mater 6(3) (2007) 183-191.

[18] A.K. Geim, K.S. Novoselov, The rise of graphene, Nanoscience and Tech-nology: A Collection of Reviews from Nature Journals, World Scientific2010, pp. 11-19.

[19] C. Soldano, A. Mahmood, E. Dujardin, Production, properties and potential of graphene, Carbon 48 (2010) 2127-2150.

[20] Y. Zhu, S. Murali, W. Cai, X. Li, J.W. Suk, J.R. Potts, R.S. Ruoff, Graphene and graphene oxide: synthesis, properties, and applications, Advanced materials 22(35) (2010) 3906-3924.

[21] W. Wu, Z. Liu, L.A. Jauregui, Q. Yu, R. Pillai, H. Cao, J. Bao, Y.P. Chen, S.-S. Pei, Wafer-scale synthesis of graphene by chemical vapor deposition and its application in hydrogen sensing, Sensor Actuat B-Chem 150 (2010) 296–300.

[22] A. Ebel, M.A. Pegoraro, B. Malard, C. Tenailleau, J. Lacaze, Coarsening and dendritic instability of spheroidal graphite in high silicon cast iron under thermal cycling in the ferritic domain, Scripta Materialia 178 (2020) 86-89.

[23] X. Ni, Z. Zheng, Extinguishment of sodium fires with Graphite@Stearate core-shell structured particles, Fire Safety Journal 111 (2020) 102933.

[24] K. Shirvanimoghaddam, E. Ghasali, A. Pakseresht, S. Derakhshandeh, M. Alizadeh, T. Ebadzadeh, M. Naebe, Super hard carbon microtubes derived from natural cotton for development of high performance titanium composites, Journal of Alloys and Compounds 775 (2019) 601-616.

[25] O. Ashrafiyan, M. Saremi, A. Pakseresht, E. Ghasali, Oxidation-Protective Coatings for Carbon-Carbon Composites, Production, Properties, and Applications of High Temperature Coatings, IGI Global2018, pp. 429-446.

[26] J. Sanchís, A. Freixa, J.C. López-Doval, L.H.M.L.M. Santos, S. Sabater, D. Barceló, E. Abad, M. Farré, Bioconcentration and bioaccumulation of C60 fuller-ene and C60 epoxide in biofilms and freshwater snails (Radix sp.), Environmental Research 180 (2020) 108715.

[27] H. Nejat Pishkenari, A. Golzari, A temperature-calibrated continuum model for vibrational analysis of the fullerene family using molecular dynamics simula-tions, Applied Mathematical Modelling 80 (2020) 115-125.

[28] Z. Genene, A. Negash, B.A. Abdulahi, R.T. Eachambadi, Z. Liu, N. Van den Brande, J. D'Haen, E. Wang, K. Vandewal, W. Maes, J. Manca, W. Mammo, S. Admassie, Comparative study on the effects of alkylsilyl and alkylthio side chains on the performance of fullerene and non-fullerene polymer solar cells, Organic Electronics 77 (2020) 105572.

[29] L. Bazli, M. Siavashi, A. Shiravi, A Review of Carbon Nanotube/TiO₂ Composite Prepared via Sol-Gel Method, Composites and Compounds 1(1) (2019).

[30] R. Maleki, H.H. Afrouzi, M. Hosseini, D. Toghraie, A. Piranfar, S. Rostami, pH-sensitive loading/releasing of doxorubicin using single-walled carbon nano-tube and multi-walled carbon nanotube: A molecular dynamics study, Computer Methods and Programs in Biomedicine 186 (2020) 105210.

[31] Y.V. Fedoseeva, L.G. Bulusheva, V.O. Koroteev, J.Y. Mevellec, B.V. Senkovs-kiy, E. Flahaut, A.V. Okotrub, Preferred attachment of fluorine near oxygen-con-taining groups on the surface of double-walled carbon nanotubes, Applied Surface Science 504 (2020) 144357.

[32] M.C. Martinez-Ballesta, N. Chelbi, A. Lopez-Zaplana, M. Carvajal, Discerning the mechanism of the multiwalled carbon nanotubes effect on root cell water and nutrient transport, Plant Physiology and Biochemistry 146 (2020) 23-30.
[33] M. Ahmaruzzaman, D. Mohanta, A. Nath, Environmentally benign fabrication of SnO₂-CNT nanohybrids and their multifunctional efficiency as an adsorbent, catalyst and antimicrobial agent for water decontamination, Scientific Re-ports 9(1) (2019) 12935.

[34] S.A. Hussain, Comparison of Graphene and Carbon Nanotube Saturable Absorbers for Wavelength and Pulse Duration Tunability, Scientific Reports 9(1) (2019) 17282.

[35] S.A. Delbari, B. Nayebi, E. Ghasali, M. Shokouhimehr, M.S. Asl, Spark plasma sintering of TiN ceramics codoped with SiC and CNT, Ceramics International 45(3) (2019) 3207-3216.

[36] Y. Orooji, M.R. Derakhshandeh, E. Ghasali, M. Alizadeh, M. Shahedi Asl, T. Ebadzadeh, Effects of ZrB₂ reinforcement on microstructure and mechanical properties of a spark plasma sintered mullite-CNT composite, Ceramics International 45(13) (2019) 16015-16021.

[37] Y. Orooji, E. Ghasali, M. Moradi, M.R. Derakhshandeh, M. Alizadeh, M.S. Asl, T. Ebadzadeh, Preparation of mullite-TiB₂-CNTs hybrid composite through spark plasma sintering, Ceramics International 45(13) (2019) 16288-16296.

[38] Y. Orooji, A.a. Alizadeh, E. Ghasali, M.R. Derakhshandeh, M. Alizadeh, M.S. Asl, T. Ebadzadeh, Co-reinforcing of mullite-TiN-CNT composites with ZrB_2 and TiB, compounds, Ceramics International 45(16) (2019) 20844-20854.

[39] P. Orsu, A. Koyyada, Recent progresses and challenges in graphene based nano materials for advanced therapeutical applications: a comprehensive review, Materials Today Communications 22 (2020) 100823.

[40] J. Yang, S. Kumar, M. Kim, H. Hong, I. Akhtar, M.A. Rehman, N. Lee, J.-Y. Park, K.B. Kim, Y. Seo, Studies on directly grown few layer graphene processed using tape-peeling method, Carbon 158 (2020) 749-755.

[41] W. Peng, K. Sun, Effects of Cu/graphene interface on the mechanical properties of multilayer Cu/graphene composites, Mechanics of Materials 141 (2020) 103270.

[42] A. Begum, M. Bose, G. Moula, Graphene Supported Rhodium Nanoparticles for Enhanced Electrocatalytic Hydrogen Evolution Reaction, Scientific Reports 9(1) (2019) 17027.

[43] E. Ghasali, M. Alizadeh, A.H. Pakseresht, T. Ebadzadeh, Preparation of sili-con carbide/carbon fiber composites through high-temperature spark plasma sin-tering, Journal of Asian Ceramic Societies 5(4) (2017) 472-478.

[44] K. Shirvanimoghaddam, S.U. Hamim, M.K. Akbari, S.M. Fakhrhoseini, H. Khayyam, A.H. Pakseresht, E. Ghasali, M. Zabet, K.S. Munir, S. Jia, Carbon fiber reinforced metal matrix composites: Fabrication processes and properties, Composites Part A: Applied Science and Manufacturing 92 (2017) 70-96.

[45] K.S. Novoselov, A.K. Geim, S.V. Morozov, D. Jiang, Y. Zhang, S.V. Dubonos, I.V. Grigorieva, A.A. Firsov, electric field effect in atomically thin carbon films, Science 306(5696) (2004) 666-9.

[46] J. Ota, S. Hait, M. Sastry, S. Ramakumar, Graphene dispersion in hydrocarbon medium and its application in lubricant technology, RSC Advances 5(66) (2015) 53326-53332.

[47] W. Yu, H. Xie, X. Wang, X. Wang, Significant thermal conductivity enhance-ment for nanofluids containing graphene nanosheets, Physics Letters A 375(10) (2011) 1323-1328.

[48] T.T. Baby, S. Ramaprabhu, Enhanced convective heat transfer using graphene dispersed nanofluids, Nanoscale research letters 6(1) (2011) 289.

[49] X. Feng, S. Kwon, J.Y. Park, M. Salmeron, Superlubric sliding of graphene nanoflakes on graphene, ACS nano 7(2) (2013) 1718-1724.

[50] K. Kim, H. Lee, C. Lee, Lee, SK, Jang, H., Ahn, JH, Kim, JH, Lee, HJ,", Chemical vapor deposition-grwon graphene: the thinnest solid lubricant", ACS Nano 5(6) (2011) 5107-5114.

[51] D. Berman, A. Erdemir, A.V. Sumant, Few layer graphene to reduce wear and friction on sliding steel surfaces, Carbon 54 (2013) 454-459.

[52] D. Berman, A. Erdemir, A.V. Sumant, Graphene: a new emerging lubricant, Materials Today 17(1) (2014) 31-42.

[53] A. Altuntepe, A. Seyhan, R. Zan, Graphene for Si-based solar cells, Journal of Molecular Structure 1200 (2020) 127055.

[54] U. Mehmood, H. Asghar, F. Babar, M. Younas, Effect of graphene contents in polyaniline/graphene composites counter electrode material on the photovolta-ic performance of dye-sensitized solar cells (DSSCSs), Solar Energy 196 (2020) 132-136.

[55] M. Masjedi-Arani, M. Ghiyasiyan-Arani, O. Amiri, M. Salavati-Niasari, CdSnO3-graphene nanocomposites: Ultrasonic synthesis using glucose as capping agent and characterization for electrochemical hydrogen storage, Ultrasonics Sonochemistry 61 (2020) 104840.

[56] Z. Zhang, Z. Gao, R. Fang, H. Li, W. He, C. Du, UV-assisted room tempera-ture NO₂ sensor using monolayer graphene decorated with SnO₂ nanoparticles, Ceramics International 46(2) (2020) 2255-2260.

[57] Y. Zhou, M. Ma, H. He, Z. Cai, N. Gao, C. He, G. Chang, X. Wang, Y. He, Highly sensitive nitrite sensor based on AuNPs/RGO nanocomposites modified graphene electrochemical transistors, Biosensors and Bioelectronics 146 (2019) 111751.

[58] Y. Long, P. He, R. Xu, T. Hayasaka, Z. Shao, J. Zhong, L. Lin, Molybde-num-carbide-graphene composites for paper-based strain and acoustic pressure sensors, Carbon 157 (2020) 594-601.

[59] M. Zhang, J.T.W. Yeow, A flexible, scalable, and self-powered mid-infrared detector based on transparent PEDOT: PSS/graphene composite, Carbon 156 (2020) 339-345.

[60] S. Gao, R. Wang, Y. Bi, H. Qu, Y. Chen, L. Zheng, Identification of frozen/ thawed beef based on label-free detection of hemin (Iron Porphyrin) with solution-gated graphene transistor sensors, Sensors and Actuators B: Chemical (2019) 127167.

[61] L. Guardia, M.J.F. ndez-Merino, J.I. Paredes, P.S.s.-F. ndez, S. Villar-Rodil, A. Martı 'nez-Alonso, J.M.D. Tasco 'n, High-throughput production of pristine graphene in an aqueous dispersion assisted by non-ionic surfactants, Carbon 49 (2011) 1653-1662.

[62] A. Ilyin, N. Guseinov, A. Nikitin, I. Tsyganov, Characterization of thin graphite layers and graphene by energy dispersive X-ray analysis, Phisica E 42 (2010) 2078–2080.

[63] M.V. Antisari, A. Montone, N. Jovic, E. Piscopiello, C. Alvania, L. Pilloni, Low energy pure shear milling: A method for the preparation of graphite na-nosheets, Scripta Mater 55 (2006) 1047–1050.

[64] G. Kalita, K. Wakita, M. Umeno, Mono layer graphene from a green solid precursor, phisica E 43(8) (2011) 1490-3.

[65] W. Chen, L. Yan, P.R. Bangal, Preparation of graphene by the rapid and mild thermal reduction of graphene oxide induced by microwaves, Carbon 48 (2010) 1146-1152.

[66] V. Sridhar, J.H. Jeon, I.K. Oh, Synthesis of graphene nano-sheets using eco-friendly chemicals and microwave radiation, Carbon 48 (2010) 2953-7.

[67] Z.Y. Juang, C.Y. Wu, C.W. Lo, W.Y. Chen, C.F. Huang, J.C. Hwang, F.R. Chen, K.C. Leou, C.H. Tsai, Synthesis of graphene on silicon carbide substrates at low temperature, Carbon 47 (2009) 2026-2031.

[68] C.-D. Kim, Y.-S. Sohn, Growth of Ni-Graphite Core-Shell for Electrode Applications, Journal of Nanoelectronics and Optoelectronics 12(6) (2017) 622-624.
[69] A. Ngqalakwezi, D. Nkazi, G. Seifert, T. Ntho, Effects of reduction of graphene oxide on the hydrogen storage capacities of metal graphene nanocomposite, Catalysis Today 358 (2020) 338-344.

[70] Y. Liu, J. Yu, D. Guo, Z. Li, Y. Su, $Ti_3C_2T_x$ MXene/graphene nanocomposites: Synthesis and application in electrochemical energy storage, Journal of Alloys and Compounds 815 (2020) 152403.

[71] A. Verma, A. Parashar, M. Packirisamy, Role of Chemical Adatoms in Fracture Mechanics of Graphene Nanolayer, Materials Today: Proceedings 11 (2019) 920-924.

[72] A.T. Johnson, Z. Luo, Large-scale graphene sheet: articles, compositions, methods and devices incorporating same, Google Patents, 2019.

[73] S.-M. Kim, W. Kim, Y. Hwangbo, J.-H. Kim, S.M. Han, Electrodeposition Cu and roll transfer of graphene for large scale fabrication of Cu-graphene nanolay-ered composite, 2D Materials 6(4) (2019) 045051.

[74] Z. Chen, W. Ren, B. Liu, L. Gao, S. Pei, Z.-S. Wu, J. Zhao, H.-M. Cheng, Bulk growth of mono- to few-layer graphene on nickel particles by chemical vapor deposition from methane, Carbon 48 (2010) 3543-3550.

[75] C. Knieke, A. Berger, M. Voigt, R.N.K. Taylor, J.R. hrl, W. Peukert, Scalable production of graphene sheets by mechanical delamination, Carbon 48 (2010) 3196-3204.

[76] W. Liu, C.H. Chung, C.Q. Miao, Y.J. Wang, B.Y. Li, L.Y. Ruan, K. Patel, Y.J. Park, J. Woo, Y.H. Xie, Chemical vapor deposition of large area few layer graphene on Si catalyzed with nickel films, Thin Solid Films 518 (2010) S128-S132.

[77] L. Zhao, K.T. Rim, H. Zhou, R. He, T.F. Heinz, A. Pinczuk, G.W. Flynn, A.N. Pasupathy, Influence of copper crystal surface on the CVD growth of large area monolayer graphene, Solid State Commun 151 (2011) 509-13.

[78] D. Wei, J. Yu, H. Huang, Y. Zhao, F. Wang, A simple quenching method for preparing graphenes, Mater lett 66 (2012) 150-2.

[79] C. Moreno, M. Vilas-Varela, B. Kretz, A. Garcia-Lekue, M.V. Costache, M. Paradinas, M. Panighel, G. Ceballos, S.O. Valenzuela, D. Peña, A. Mugarza, Bottom-up synthesis of multifunctional nanoporous graphene, Science 360(6385) (2018) 199.

[80] C. Bronner, R.A. Durr, D.J. Rizzo, Y.-L. Lee, T. Marangoni, A.M. Kalayji-an, H. Rodriguez, W. Zhao, S.G. Louie, F.R. Fischer, M.F. Crommie, Hierarchical On-Surface Synthesis of Graphene Nanoribbon Heterojunctions, ACS Nano 12(3) (2018) 2193-2200.

[81] J.Y. Lim, N.M. Mubarak, E.C. Abdullah, S. Nizamuddin, M. Khalid, In-amuddin, Recent trends in the synthesis of graphene and graphene oxide based nanomaterials for removal of heavy metals — A review, Journal of Industrial and Engineering Chemistry 66 (2018) 29-44.

[82] M.V. Antisari, A. Montone, N. Jovic, E. Piscopiello, C. Alvani, L. Pilloni, Low energy pure shear milling: a method for the preparation of graphite nano-sheets, Scripta Materialia 55(11) (2006) 1047-1050.

[83] J. Chen, M. Duan, G. Chen, Continuous mechanical exfoliation of graphene sheets via three-roll mill, Journal of Materials Chemistry 22(37) (2012) 19625-19628.

[84] F.A. Litt, Lubricant additives-chemistry and applications, Marcel Dekker, Inc., New York, NY (2003) 357-358.

[85] S. Choudhary, H.P. Mungse, O.P. Khatri, Dispersion of alkylated graphene in organic solvents and its potential for lubrication applications, Journal of Materials Chemistry 22(39) (2012) 21032-21039.

[86] T. Kuila, S. Bose, C.E. Hong, M.E. Uddin, P. Khanra, N.H. Kim, J.H. Lee, Preparation of functionalized graphene/linear low density polyethylene compos-ites by a solution mixing method, Carbon 49(3) (2011) 1033-1037.

[87] W. Zhang, M. Zhou, H. Zhu, Y. Tian, K. Wang, J. Wei, F. Ji, X. Li, Z. Li, P. Zhang, Tribological properties of oleic acid-modified graphene as lubricant oil additives, Journal of Physics D: Applied Physics 44(20) (2011) 205303.

[88] M.S. Dresselhaus, A. Jorio, M. Hofmann, G. Dresselhaus, R. Saito, Perspec-tives on Carbon Nanotubes and Graphene Raman Spectroscopy, Nano Letters 10(3) (2010) 751-758.