

Available online at www.jourcc.com

Journal homepage: www.JOURCC.com



# Journal of Composites and Compounds

## Determination of Hg<sup>2+</sup> by diphenylcarbazone compound in polymer film

### Asghar Kazemzadeh<sup>a</sup>\*, Houman Kazemzadeh<sup>b</sup>

<sup>a</sup> Department of Nanotechnology & Advanced Materials, Materials and Energy Research Center, Karaj, Iran <sup>b</sup> Faculty of Pharmacy, Tehran University of Medical Science, Tehran, Iran

#### ABSTRACT

#### ARTICLEINFORMATION

A sensitive optical sensor for determining Hg<sup>2+</sup> concentration has been prepared by incorporating the indicator Article history: dye, diphenylcarbazone compound, into cellulose acetate polymer film. To prepare the sensor, a cellulose acetate Received 5 October 2019 film was hydrolyzed with base and then the diphenylcarbazone compound bonded to the film. This method is easy to perform and uses acetyl cellulose as a carrier. According to the results, the prepared sensor was able to determine the Hg<sup>2+</sup> concentration with a  $\pm 6\%$  error. Also, the adsorption capacity was  $3.41 \times 10^{-3}$  mmol/g. ©2019 JCC Research Group.

Peer review under responsibility of JCC Research Group.

Received in revised form 20 November 2019 Accepted 29 December 2019

#### Keywords:

Optical sensor Mercury determination Diphenylcarbazone compound Cellulose acetate

#### 1. Introduction

One of the most popular poisonous elements in aquatic ecosystems is mercury (Hg2+) in a way that even a low amount of this element can significantly affect human health [1-8]. This is due to the Hg<sup>2+</sup> accumulation in the human body from the food chain which causes serious damages to the brain, lungs, central nervous system, kidney, and the development of the fetus [9-14]. Unfortunately, the emission of mercury by humans is increasing [15, 16]. This increasing trend in environmental pollution is considered a global concern. For addressing this issue, a reliable and rapid method is needed to determine the mercury trace [17].

In this respect, a variety of sensitive analytical methods can be used to determine Hg2+ selectively such as inductively coupled plasma-atomic emission spectrometry (ICP-AES), inductively coupled plasma mass spectrometry (ICP-MS) [18, 19], cold-vapor atomic fluorescence spectroscopy (CVAFS) [20], and cold-vapor atomic absorption spectroscopy (CVAAS) [21-23]. Although these traditional techniques are sensitive with high accuracy, the measurement instruments are sophisticated, expensive, with high costs of operation, and the sample preparation process is complicated. These factors make these methods time-consuming for a large number of samples and are not unsuitable for routine monitoring in the field. Besides, during the collection, samples may be altered. Consequently, the design of an inexpensive, fast technique for the detection of Hg2+ is desired. Currently, some techniques are employed for field application and miniaturization including fluorimetry and colorimetry [24-31]. However, their application is still limited due to the interference of other metal ions and sophisticated synthesis of probe materials [32, 33]. Voltammetric methods which are electrochemical techniques have a high potential for the determination of Hg2+ in the field compared to other methods [34, 35]. This is because of possessing some inherent characteristics, including selectivity and sensitivity, miniaturization, cost-effectiveness, and rapid analysis time [36].

So far, in spite of the increasing interest in the development of a time-saving, easy-to-operate, low-cost, and reliable technique for the determination of Hg<sup>2+</sup> in the field, only a few numbers of studies have addressed the optical sensors (fluorescent and colorimetric) [25, 37, 38]. Some studies have been worked on the determination of Hg2+ through voltammetric methods, but they are fragmentary and incompletely [39-41]. To the best knowledge of the authors, none of the previous studies have focused particularly on the determination of Hg2+ through voltammetric techniques. Moreover, the application of nanomaterials in these methods has been recently gained increasing attention. This research focuses on the preparation of a highly sensitive sensor for determining Hg2+ concentration by incorporating the indicator dye, diphenylcarbazone compound, into a polymer film.

#### 2. Experiment Procedure

#### 2.1. Materials

To prepare a standard solution of mercury chloride (HgCl., 0.1 M), 2.715 g of HgCl, dissolved in 100 ml distilled water in a standard flask. Diphenylcarbazone compound 0.02% solution was prepared by dissolv-

\* Corresponding author: Asghar Kazemzadeh; E-mail:asg642001@yahoo.com DOR: 20.1001.1.26765837.2019.1.1.5.4

https://doi.org/10.29252/icc.1.1.5 This is an open access article under the CC BY license (https://creativecommons.org/licenses/by/4.0)



Fig. 1. The possible reaction between the activated membrane and diphenylcarbazone compound.



Fig. 3. Adsorption of Hg2+ in different pH values.

ing the C<sub>2</sub>H<sub>5</sub>OH dye solution with a 2.00% concentration in a 100 ml volumetric flask. 2.264 g NH<sub>4</sub>Cl was dissolved in 100 ml distilled water to prepare NH<sub>4</sub>Cl solution with 0.4 M concentration and 2.14 g NaBrO<sub>3</sub> was dissolved in distilled water in a volumetric flask (250 ml) to obtain NaBrO<sub>3</sub> solution with 0.06 M concentration. For the preparation of polyvinyl alcohol and Thiourea solutions, 0.7 g and 1g of the reagents were dissolved in 100 ml of distilled water, respectively.

#### 2.2. Methods

#### 2.2.1. Sensor Preparation

For de-esterification of the acetyl group and the increase in the membrane porosity, the hydrolysis of acetyl cellulose was carried out. The transparent films were immersed in KOH (0.1 mol.1<sup>-1</sup>) for 24 hours. Subsequently, the specimens were washed with distilled water followed by the treatment with a mixture of polyvinyl alcohol (0.70 % (w/v)) and thiourea (1.00 % (w/v)) solution for 48 hours at room temperature. Then, the polymer membrane was treated with a solution of diphenylcarbazone compound (0.020 % (w/v)) at room temperature and stirred for about 20 hours. At the next step, the film was washed by rinsing with distilled water to the extent that no absorbance was observed at the dye wavelength. The drying process of the film was carried out at 45 °C for 15 minutes.

#### 2.2.2. Spectrophotometric Measurements

Shimadzu 2100 ultraviolet-visible (UV-Vis) spectrophotometer and a thermostated cell were used to measure the UV-Vis spectra at the con-

Table 1.

The standard amount of Hg <sup>2+</sup> (ng)	The measured amount of $Hg^{2+}$ by the proposed Mean $\pm$ SD method (ng)			
10	9	12	11	$10.6\pm0.1$
20	22	18	23	$21\pm0.1$
25	23	26	27	$25.3\pm0.1$



Fig. 2. UV-Vis spectrum of the polymer film functionalized with diphenylcarbazone compound.

trolled temperature of 25 °C  $\pm$  0.1.

#### 3. Results and Discussion

The reaction between the activated cellulose film and the diphenylcarbazone compound is illustrated in Fig. 1. There is an amino group in the structure of the diphenylcarbazone compound, therefore, by special treatments, the molecules of the dye can be linked to cellulose acetate. According to Kostov et al. [42], just the dyes that have amino groups in their structure are able to be linked to cellulose acetate. With the help of thiourea, it is possible to link dyes with or without amino groups in their structure to cellulose acetate polymer.

As a result of the high activity of the carrier, the interaction of the carrier compounds having the low molecular weight and a free para-position in their structure is possible.

Therefore, indicators with a free para-position or hydroxyl group in their molecule can be employed. In addition, to link the molecules of dye to the cellulose acetate membrane, thiourea acts as a bridge. This results in the covalent bonding between the indicator and the polymer film [43]. BrO<sup>3-</sup> can oxidize diphenylcarbazone compound in the presence of Hg<sup>2+</sup> in an acidic environment (pH ~ 4.5) [44].

#### 3.1. UV-Vis Spectrum of Functionalized Cellulose Acetate

The UV-Vis spectrum of the treated cellulose acetate was obtained by measuring the intensity at a different wavelength and plotted against wavelength. The UV-Vis spectrum of the diphenylcarbazone-functionalized film obtained is shown in Fig. 2. As illustrated, the maximum absorption appeared at 480 nm. Thus, the spectrophotometric measurements were carried out at 480 nm.

#### 3.2. The Effect of pH on the Adsorption of Hg<sup>2+</sup>

The acidity of the solution affects the  $Hg^{2+}$  determination sensitivity of the diphenylcarbazone compound. The adsorption plot versus pH for the functionalized polymer film is shown in Fig. 3. The pH value was adjusted with sodium hydroxide or hydrochloric acid at an  $Hg^{2+}$ concentration of  $1.0 \times 10^{-5}$  mol/mL and the amount of adsorbed Hg was measured by spectroscopy. The adsorption of  $Hg^{2+}$  decreases for a pH value of lower than 5. Decreasing the pH of the solution reduces the adsorption of the diphenylcarbazone compound. However, in neutral solutions, the interfering of other heavy ions increases and they produce colored compositions with diphenylcarbazone compound. When acidity increases, the diphenylcarbazone-mercury complex formed on the polymer film gradually decomposes and decolorizes [45, 46]. Therefore the determination measurement was carried out at pH = 5.

3.3. Determination of Micro-amounts of Hg<sup>2+</sup> by UV-Vis Spectroscopy



Fig. 4. Calibration curve for Hg at the wavelength of 480 nm.

The signal intensity of UV-Vis spectroscopy of the specimen was investigated at 480 nm for different Hg<sup>2+</sup> concentrations in the range of 0 to 25 ng/mL to obtain the calibration curve. The calibration curve obtained is linear from 0 to 25 ng as shown in Fig. 4. Three measurements for each absorption value for each solution were carried out and the mean value was reported. By employing the plotted calibration curve, the determination of unknown concentrations of mercury was performed. The results of measurements with the prepared sample are summarized in Table 1. The error of the measurements was within  $\pm 6\%$  for samples 10 to 25 ng.

# 3.4. Adsorption Isotherm of $Hg^{2+}$ on the Functionalized Cellulose Acetate Film

Fig. 5 illustrates the optical characteristics of the immobilized diphenylcarbazone compound on the cellulose acetate film for different concentrations of Hg<sup>2+</sup>. To evaluate the binding capacity of the functionalized polymer film, a rebinding experiment was carried out by using 0.2 g of the polymer film in 25 mL phosphate buffer solution of HgCl<sub>2</sub> (pH ~ 4). The suspension was stirred at 25 °C for 30 minutes and the absorption amount in the range of 0 to 200  $\mu$ g/25mL was measured. After the exposure to the solution, the polymer film was removed from the solution and the concentration of remaining Hg<sup>2+</sup> was analyzed. The mercury amount adsorbed on the surface of the functionalized polymer was calculated by Eq. (1):

 $Q = C_i - C_e$ 

where  $C_e$  and  $C_i$  denote the equilibrium and initial concentrations of Hg<sup>2+</sup> (25 µg/mL), respectively [47]. Fig. 4 shows the obtained results of the adsorbed Hg<sup>2+</sup>. It is evident that with increasing the concentration of Hg<sup>2+</sup> in solutions from 0 to 150 µg/25mL, the amount of Hg<sup>2+</sup> adsorbed by the functionalized cellulose acetate increased linearly. According to the adsorption curve, the functionalized cellulose acetate film has the maximum adsorption capacity of Hg<sup>2+</sup> equal to  $3.41 \times 10^{-3}$  mmol/g.

#### 4. Conclusions

One of the most popular poisonous elements in aquatic ecosystems is mercury and the design of a reliable and rapid method for determination of mercury is needed. In this research, an optical sensor was prepared by the functionalization of hydrolyzed cellulose acetate by diphenylcarbazone.

The UV-Vis spectra of the polymer film showed a peak at 480 nm. The maximum adsorption was achieved at pH = 5 and by the decrease in pH, the adsorption decreased. Using the calibration curve, the error in determining the concentration of  $Hg^{2+}$  was around 6 %. The film exhibited the capability of the adsorption capacity in a wide range of  $Hg^{2+}$  concentration.



Fig. 5. Hg adsorption of the functionalized cellulose acetate film.

#### Acknowledgments

The authors thank the Materials & Energy Research Center, Karaj, Iran, for its financial and other support.

#### **Conflict of Interest**

All authors declare no conflicts of interest in this paper.

#### REFERENCES

(1)

[1] I. Hofer, M. Gremaud, A. Marchese, S. Le Bouhellec, Determination of Mercury in Aerosol by Inductively Coupled Plasma Mass Spectrometry, Beiträge zur Tabakforschung International/Contributions to Tobacco Research 27(8) (2017) 186-194.

[2] L. Yang, Y. Zhang, F. Wang, Z. Luo, S. Guo, U. Strähle, Toxicity of mercury: Molecular evidence, Chemosphere 245 (2020) 125586.

[3] S. Koli, A. Prakash, S. Choudhury, R. Mandil, S.K. Garg, Mercury affects uter-ine myogenic activity even without producing any apparent toxicity in rats: In-volvement of calcium-signaling cascades, Journal of Trace Elements in Medicine and Biology 57 (2020) 40-47.

[4] J. Kim, H. Lee, G. Park, H. Choi, S. Ji, D. Kil, Determination of the Toxic Level of Dietary Mercury and Prediction of Mercury Intake and Tissue Mercury Concentrations in Broiler Chickens Using Feather Mercury Concentrations, The Journal of Applied Poultry Research 28(4) (2019) 1240-1247.

[5] P. Oliveira, A.V. Lírio, C. Canhoto, L. Guilhermino, Toxicity of mercury and post-exposure recovery in Corbicula fluminea: Neurotoxicity, oxidative stress and oxygen consumption, Ecological Indicators 91 (2018) 503-510.

[6] C.M. Bulka, P.A. Bommarito, R.C. Fry, Predictors of toxic metal exposures among US women of reproductive age, Journal of Exposure Science & Environmental Epidemiology 29(5) (2019) 597-612.

[7] S. Vennam, S. Georgoulas, A. Khawaja, S. Chua, N.G. Strouthidis, P.J. Foster, Heavy metal toxicity and the aetiology of glaucoma, Eye 34(1) (2020) 129-137.

[8] M.A. Al-Ghouti, D. Da'ana, M. Abu-Dieyeh, M. Khraisheh, Adsorptive remov-al of mercury from water by adsorbents derived from date pits, Scientific reports 9(1) (2019) 1-15.

[9] S.A. El-Safty, M. Shenashen, Mercury-ion optical sensors, TrAC Trends in Analytical Chemistry 38 (2012) 98-115.

[10] S. Cinnirella, D. Bruno, N. Pirrone, M. Horvat, I. Živković, D. Evers, S. Johnson, E. Sunderland, Mercury concentrations in biota in the Mediterranean Sea, a compilation of 40 years of surveys, Scientific data 6(1) (2019) 1-11.

[11] F. Kahrizi, A. Salimi, F. Noorbakhsh, M. Faizi, F. Mehri, P. Naserzadeh, N. Naderi, J. Pourahmad, Repeated administration of mercury intensifies brain damage in multiple sclerosis through mitochondrial dysfunction, Iranian journal of pharmaceutical research: IJPR 15(4) (2016) 834.

[12] R. Raghuvanshi, A. Chaudhari, G.N. Kumar, Amelioration of cadmium-and mercury-induced liver and kidney damage in rats by genetically engineered pro-biotic Escherichia coli Nissle 1917 producing pyrroloquinoline quinone with oral supplementation of citric acid, Nutrition 32(11-12) (2016) 1285-1294.

[13] M.N. Rana, J. Tangpong, M.M. Rahman, Toxicodynamics of lead, cadmium, mercury and arsenic-induced kidney toxicity and treatment strategy: a mini review, Toxicology reports 5 (2018) 704-713. [14] S. Orr, Potential Mechanisms of Inorganic Mercury Intoxication in Rat Kidney Cells, Mercer University, 2018.

[15] D.G. Streets, Q. Zhang, Y. Wu, Projections of global mercury emissions in 2050, Environmental science & technology 43(8) (2009) 2983-2988.

[16] F. Amélineau, D. Grémillet, A.M. Harding, W. Walkusz, R. Choquet, J. Fort, Arctic climate change and pollution impact little auk foraging and fitness across a decade, Scientific reports 9(1) (2019) 1014.

[17] B. Smolińska, The influence of compost and nitrilotriacetic acid on mercury phytoextraction by Lepidium sativum L, Journal of Chemical Technology & Bio-technology 95(4) (2020) 950-958.

[18] K. Leopold, M. Foulkes, P. Worsfold, Methods for the determination and speciation of mercury in natural waters—a review, Analytica chimica acta 663(2) (2010) 127-138.

[19] M. de Godoi Pereira, M.A.Z. Arruda, Trends in preconcentration procedures for metal determination using atomic spectrometry techniques, Microchimica Acta 141(3-4) (2003) 115-131.

[20] W. Geng, T. Nakajima, H. Takanashi, A. Ohki, Determination of mercury in ash and soil samples by oxygen flask combustion method–cold vapor atomic fluo-rescence spectrometry (CVAFS), Journal of hazardous materials 154(1-3) (2008) 325-330.

[21] J. Górecki, P. Burmistrz, M. Trzaskowska, B. Sołtys, J. Gołaś, Method devel-opment and validation for total mercury determination in coke oven gas combining a trap sampling method with CVAAS detection, Talanta 188 (2018) 293-298.

[22] X. Lu, J. Zhao, X. Liang, L. Zhang, Y. Liu, X. Yin, X. Li, B. Gu, The Applica-tion and Potential Artifacts of Zeeman Cold Vapor Atomic Absorption Spectrom-etry in Mercury Stable Isotope Analysis, Environmental Science & Technology Letters 6(3) (2019) 165-170.

[23] M. Głogowska, R. Stawarz, Accumulation of mercury in women in relation age and state of health, Journal of Microbiology, Biotechnology and Food Sciences 2019 (2019) 19.

[24] G. Aragay, J. Pons, A. Merkoçi, Recent trends in macro-, micro-, and nano-material-based tools and strategies for heavy-metal detection, Chemical reviews 111(5) (2011) 3433-3458.

[25] H.N. Kim, W.X. Ren, J.S. Kim, J. Yoon, Fluorescent and colorimetric sensors for detection of lead, cadmium, and mercury ions, Chemical Society Reviews 41(8) (2012) 3210-3244.

[26] S. Yoon, A.E. Albers, A.P. Wong, C.J. Chang, Screening mercury levels in fish with a selective fluorescent chemosensor, Journal of the American Chemical Society 127(46) (2005) 16030-16031.

[27] L. Feng, Y. Zhang, L. Wen, Z. Shen, Y. Guan, Colorimetric determination of copper (II) ions by filtration on sol–gel membrane doped with diphenylcarbazide, Talanta 84(3) (2011) 913-917.

[28] G. Peng, Y. Chen, R. Deng, Q. He, D. Liu, Y. Lu, J.-M. Lin, Highly sensitive and selective determination of Hg (II) based on microfluidic chip with on-line flu-orescent derivatization, Spectrochimica Acta Part A: Molecular and Biomolecular Spectroscopy 204 (2018) 1-6.

[29] D. Huang, X. Liu, C. Lai, L. Qin, C. Zhang, H. Yi, G. Zeng, B. Li, R. Deng, S. Liu, Colorimetric determination of mercury (II) using gold nanoparticles and double ligand exchange, Microchimica Acta 186(1) (2019) 31.

[30] H. Xia, C. Li, H. Chen, Green preparation of CuI particles in dielectric bar-rier discharge for colorimetric determination of trace mercury in comparison with atomic fluorescence spectrometric determination, Microchemical Journal 146 (2019) 1169-1172.

[31] C. Wang, G. Tang, H. Tan, Colorimetric determination of mercury (II) via the inhibition by ssDNA of the oxidase-like activity of a mixed valence state ceri-umbased metal-organic framework, Microchimica Acta 185(10) (2018) 475.

[32] E. Soršak, J. Volmajer Valh, Š. Korent Urek, A. Lobnik, Design and Investi-gation of Optical Properties of N-(Rhodamine-B)-Lactam-Ethylenediamine (RhB-EDA) Fluorescent Probe, Sensors 18(4) (2018) 1201.

[33] M. Saqib, S. Bashir, H. Li, C. Li, S. Wang, Y. Jin, Efficient Electrogenerated Chemiluminescence of Tris (2, 2'-bipyridine) ruthenium (II) with N-Hydroxysul-fosuccinimide as a Coreactant for Selective and Sensitive Detection of I-Proline and Mercury (II), Analytical chemistry 91(19) (2019) 12517-12524.

[34] M. Tsetsoni, E. Roditi, C. Kokkinos, A. Economou, Microfabricated Au-Film Sensors for the Voltammetric Determination of Hg (II), Multidisciplinary Digital Publishing Institute Proceedings 2(13) (2018) 1518.

[35] Y. Zhang, R. Qiao, C. Sheng, H. Zhao, Technologies for detection of HRPs in wastewater, High-Risk Pollutants in Wastewater, Elsevier2020, pp. 79-100.

[36] A. Waheed, M. Mansha, N. Ullah, Nanomaterials-based electrochemical detection of heavy metals in water: current status, challenges and future direction, TrAC Trends in Analytical Chemistry 105 (2018) 37-51.

[37] Y.-W. Lin, C.-C. Huang, H.-T. Chang, Gold nanoparticle probes for the detec-tion of mercury, lead and copper ions, Analyst 136(5) (2011) 863-871.

[38] P.D. Selid, H. Xu, E.M. Collins, M. Striped Face-Collins, J.X. Zhao, Sensing mercury for biomedical and environmental monitoring, Sensors 9(7) (2009) 5446-5459.

[39] L. Rassaei, F. Marken, M. Sillanpää, M. Amiri, C.M. Cirtiu, M. Sillanpää, Nanoparticles in electrochemical sensors for environmental monitoring, TrAC Trends in Analytical Chemistry 30(11) (2011) 1704-1715.

[40] A. Economou, Recent developments in on-line electrochemical stripping analysis—An overview of the last 12 years, Analytica Chimica Acta 683(1) (2010) 38-51.

[41] N.Y. Stozhko, N.A. Malakhova, M.V. Fyodorov, K.Z. Brainina, Modified carbon-containing electrodes in stripping voltammetry of metals, Journal of Solid State Electrochemistry 12(10) (2008) 1185-1204.

[42] Y. Kostov, A. Neykov, Rapid Covalent Method for Fabrication of Optical pH Sensitive Membranes, Analytical Letters 33(3) (2000) 413-423.

[43] Y. Jiang, H. Zhang, Q. He, Z. Hu, X. Chang, Selective solid-phase extraction of trace mercury (II) using a silica gel modified with diethylenetriamine and thiourea, Microchimica Acta 178(3-4) (2012) 421-428.

[44] M. Otto, J. Stach, R. Kirmse, Mechanism and kinetics of the vanadium-cata-lyzed o-dianisidine—t-butyl hydroperoxide reaction in non-aqueous media, Ana-lytica Chimica Acta 147 (1983) 277-286.

[45] O. Güney, F.Ç. Cebeci, Molecularly imprinted fluorescent polymers as che-mosensors for the detection of mercury ions in aqueous media, Journal of applied polymer science 117(4) (2010) 2373-2379.

[46] J. Fan, Y. Qin, C. Ye, P. Peng, C. Wu, Preparation of the diphenylcarba-zone-functionalized silica gel and its application to on-line selective solid-phase extraction and determination of mercury by flow-injection spectrophotometry, Journal of hazardous materials 150(2) (2008) 343-350.

[47] L. Mergola, S. Scorrano, E. Bloise, M.P. Di Bello, M. Catalano, G. Vasapollo, R. Del Sole, Novel polymeric sorbents based on imprinted Hg (II)-diphenylcarba-zone complexes for mercury removal from drinking water, Polymer Journal 48(1) (2016) 73.